

Medium – Clear



Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temp.	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
Recommended for all grades and types of Carlton PVC conduit, duct, wireway and fittings, except Flex-Plus® Blue™ ENT (Electrical Non-metallic Tubing.) Up through 6" diameter.	Under -12°C not recommended -1 to 10°C 5-6 minutes 10 to 21°C 3-4 minutes 21 to 32°C 1-2 minutes	5 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	500-900 cps

Cat. No.	Size	Applicator	Description	Ctn Qty	Ctn Wt. (lb)
VC9963C	473 ml	Dauber	PVC Medium Clear	24	29.0
VC9962	946 ml	Dauber	PVC Medium Clear	12	27.5
VC9961P	3.78 l	-	PVC Medium Clear	6	53.5


Regular – Clear



Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temp.	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
Recommended for all grades and types of Carlton PVC conduit, duct, wireway and fittings, except Flex-Plus® Blue™ ENT (Electrical Non-metallic Tubing.) Up through 6" diameter.	Under -12°C not recommended -1 to 10°C 5-6 minutes 10 to 21°C 3-4 minutes 21 to 32°C 1-2 minutes	5 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	500-900 cps

Cat. No.	Size	Applicator	Description	Ctn Qty	Ctn Wt. (lb)
VC9964	237 ml	Dauber	PVC Regular Clear	10	10.0
VC9965C	118 ml	Dauber	PVC Regular Clear	24	8.4

Medium – Grey




Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temp.	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
Recommended for all grades and types of Carlton PVC conduit, duct, wireway and fittings, except Flex-Plus® Blue™ ENT (Electrical Non-metallic Tubing.) Up through 6" diameter.	Under -12°C not recommended -1 to 10°C 5-6 minutes 10 to 21°C 3-4 minutes 21 to 32°C 1-2 minutes	5 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	500-900 cps

Cat. No.	Size	Applicator	Description	Ctn Qty	Ctn Wt. (lb)
VC9923	473 ml	Dauber	PVC Medium Grey	24	29.0
VC9922	946 ml	Dauber	PVC Medium Grey	12	27.5
VC9941P	3.78 l	-	PVC Medium Grey	6	53.5

Meets ASTM D-2564

Regular – Grey



Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temp.	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
Recommended for all grades and types of Carlton PVC conduit, duct, wireway and fittings, except Flex-Plus® Blue™ ENT (Electrical Non-metallic Tubing.) Up through 6" diameter.	Under -12°C not recommended -1 to 10°C 5-6 minutes 10 to 21°C 3-4 minutes 21 to 32°C 1-2 minutes	5 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	500-900 cps

Cat. No.	Size	Applicator	Description	Ctn Qty	Ctn Wt. (lb)
VC9924-24	237 ml	Dauber	PVC Regular Grey	24	15.0

Meets ASTM D-2564