


Available Finishes / Materials:

EG -- Electro-galvanized

PL -- Plain steel

Standard Finish: PL, EG

Catalog Number		Wt. lbs	RS	T Thickness
Plain Finish	EG Finish			
CIN 0025PL	CIN 0025EG	0.11	1/4"-20	1/4"
CIN 0037PL	CIN 0037EG	0.16	3/8"-16	1/4"
CIN 0050PL	CIN 0050EG	0.20	1/2"-13	5/16"
CIN 0062PL	CIN 0062EG	0.18	5/8"-11	5/16"
CIN 0075PL	CIN 0075EG	0.17	3/4"-10	1/2"
CIN 0087PL	CIN 0087EG	0.15	7/8"-9	1/2"



Material Specifications and Finishes

Carbon Steel – ASTM A1011-00 SS GR 33 or ASTM A1011-00CS Type B

EG – Electro-Galvanized. Electroplating deposits zinc on the surface of the steel by electrolysis from a bath of zinc salts. Recommended for relatively dry indoor use. This is the standard coating for most Phoenix products. Thickness of applied zinc is between 0.2 mils to 0.5 mils [5.1 μm to 12.7 μm]. Coatings on Phoenix EG products meet ASTM B633 SC1 Type III.

PL – Plain. No coating on the steel except some oil left on the part from the pickle and oil or fabrication process.

Note: Specifications subject to change without notice.

Project:	Date:	Phone:
Submitted By:	Address:	
Comment		