

## All Weather – ENT Blue



ENT cement required for use with ENT and Rigid Non-metallic Conduit fittings

Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temperature	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
Required for use with Flex-Plus® Blue™ ENT (Electrical Non-metallic Tubing), Riser-Gard™, P&C Flex™ and Carlton PVC fittings. Up through 6" diameter.	-20 to -12°C 6-8 minutes -12 to -1°C 4-5 minutes -1 to 10°C 3-4 minutes 10 to 21°C 1-2 minutes 21 to 32°C 1/2-1-1/2 minutes	-20 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	400-700 cps

Cat. No.	Size	Applicator	Ctn Qty	Ctn Wt. (lb)
<b>VC9992</b>	946 ml	Dauber	12	29.0

Meets ASTM D-2564

## Resi-Gard® – Clear



Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temperature	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
For use with Resi-Gard®, P&C Flex™ and Carlton PVC fittings. Up through 6" diameter.	-12 to -1°C 4-5 minutes -1 to 10°C 3-4 minutes 10 to 21°C 1-2 minutes 21 to 32°C 1/2-1-1/2 minutes	5 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	500-900 cps

Cat. No.	Size	Applicator	Ctn Qty	Ctn Wt. (lb)
<b>VC9963SC</b>	473 ml	Brush	24	28.0

Meets ASTM D-2564

## All Weather – "Quick-Set" Cement




Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temperature	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
Recommended for all grades and types of Carlton PVC conduit, duct, wireway and fittings, except Flex-Plus® Blue™ ENT (Electrical Non-metallic Tubing.) Up through 6" diameter.	-20 to -12°C 6-8 minutes -12 to -1°C 4-5 minutes -1 to 10°C 3-4 minutes 10 to 21°C 1-2 minutes 21 to 32°C 1/2-1-1/2 minutes	-20 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	400-700 cps

Cat. No.	Size	Applicator	Ctn Qty	Ctn Wt. (lb)
<b>VC9984</b>	237 ml	Dauber	10	7.0
<b>VC9983C</b>	473 ml	Dauber	24	30.0
<b>VC9982</b>	946 ml	Dauber	12	29.0
<b>VC9981P</b>	3.78 l	Dauber	6	54.0
<b>VC9985C</b>	118 ml	Dauber	24	7.5

Meets ASTM D-2564

## Low VOC – Grey



Recommended pipe application and sizes	Set-up time (Evaporation Rate)	Recommended installation temp.	Lap Shear @ 23°C	Viscosity at 24°C as manufactured
Recommended for all grades and types of Carlton PVC conduit, duct, wireway and fittings, except Flex-Plus® Blue™ ENT (Electrical Non-metallic Tubing.) Up through 6" diameter. VOC emission of 490 grams/liter per the Bay and South Coast test method.	Under -1°C not recommended -1 to 10°C 5-6 minutes 10 to 21°C 3-4 minutes 21 to 32°C 1-2 minutes	5 to 37.7°C	2 hrs. 350 psi 16 hrs. 800 psi 72 hrs. 1,500 psi	500-900 cps

Cat. No.	Size	Applicator	Ctn Qty	Ctn Wt. (lb)
<b>VC9LV4-24</b>	237 ml	Dauber	24	15.5
<b>VC9LV3</b>	473 ml	Dauber	24	27.0
<b>VC9LV2</b>	946 ml	Dauber	12	26.0

Meets ASTM D-2564